



PRODUCT DATASHEET

A4 BI-METAL TEK SCREW

Product Details

Designed for:	<i>Fastening in aluminium sheeting and panels</i>
Head style:	<i>Hexagonal</i>
Drive bit:	<i>5/16" hexagonal</i>
Thread form:	<i>Twin, coarse thread (Tek 3)/fine thread (Tek 5)</i>
Material grade:	<i>A4 stainless</i>
Coating:	<i>Electroplated zinc</i>
Recommended drill speed:	<i>1500 – 2500 RPM</i>

Tek 3 range – for light steel

Product Code	Size	Drill point	Effective thread length	Drilling Capacity	Washer	Steel thickness
A4BM25-3	5.5 x 25mm	Tek 3	14.0mm	1.2 - 3.5mm	N/A	1.2 - 3.5mm
A4BM38-3	5.5 x 38mm	Tek 3	27.0mm	1.2 – 3.5mm	N/A	1.2 – 3.5mm
A4BM50-3	5.5 x 50mm	Tek 3	38.0mm	1.2 – 3.5mm	N/A	1.2 – 3.5mm
A4BM75-3	5.5 x 75mm	Tek 3	60.0mm	1.2 – 3.5mm	N/A	1.2 – 3.5mm

Tek 5 range – for heavy steel

Product Code	Size	Drill point	Effective thread length	Drilling Capacity	Washer	Steel thickness
A4BM38-5	5.5 x 38mm	Tek 5	15.0mm	4.0 – 12.5mm	N/A	4.0 – 12.5mm
A4BM50-5	5.5 x 50mm	Tek 5	30.0mm	4.0 – 12.5mm	N/A	4.0 – 12.5mm

Technical Data

Hardness Rating (Vickers scale)			Ultimate Mechanical Performance		
Diameter	Surface Hardness	Core Hardness	Diameter	Tensile Strength	Shear Strength
5.5mm	385.9HV0.3	309.7HV0.3	5.5mm	13.2kN	10.9kN

Technical Data continued...

Tek 3 range – Unfactored pull out values						
Diameter	Drill Point	Steel Thickness				
		1.2mm	1.6mm	2.0mm	2.5mm	3.0mm
5.5mm	Tek 3	1.8kN	2.2kN	2.5kN	3.4kN	4.3kN
						6.2kN

Tek 5 range – Unfactored pull out values						
Diameter	Drill Point	Steel Thickness				
		4.0mm	5.0mm	6.0mm	8.0mm	10.0mm
5.5mm	Tek 5	6.8kN	7.4kN	8.2kN	9.7kN	10.4kN
						11.9kN

ABOUT OUR TESTING

All test results were derived from empirical testing performed by ETAS (Evolution Testing & Analytical Services), a UKAS (United Kingdom Accreditation Service) accredited testing laboratory (Accreditation No. 7485). The following tests were performed to the following standards.



7485

Test/ Parameter	Standard/ Method/ Procedure
Ultimate Tensile	ISO 6892-1: 2009 “Metallic materials – tensile testing – Part 1: Method of test at room temperature”.
Ultimate Shear	MIL-STD-1312-13 “Military Standard: Fastener test method (Method 13) Double shear test”.
Pull Out (Withdrawal Force)	EN 14566: 2009 “Mechanical fasteners for gypsum plasterboard systems. Definitions, requirements and test methods”.
Pull Over	EN 14592: 2008 “Timber structures. Dowel type fasteners. Requirements”.
Hardness	ISO 650 7-1: 2005 “Metallic materials – Vickers hardness test – Part 1: Test method”.
Corrosion Resistance	EN ISO 9227: 2012 “Corrosion tests in artificial atmospheres. Salt spray tests”.
Drilling Time Test	EN 14566: 2009 “Mechanical fasteners for gypsum plasterboard systems. Definitions, requirements and test methods”.

Laboratory Contact Details

Evolution Testing & Analytical Services

Units 2A & 2B Clyde Gateway Trade Park
Dalmarnock Road
Rutherglen
South Lanarkshire
G73 1AN

T: (0141) 643 4125
F: (0141) 647 5100